



UzAuto Cepla



Sinf: CAB 21A-UZ

Texnik ma'lumotlar varaqasi

Turi: Injeksiya qoliplash, ABS

Qo'llanilishi: Oddiy maishiy texnikalar.

Xususiyatlar	Sinov usuli	O'lchov birligi	Qiymatlar
Fizik xususiyatlar			
Zichlik	ISO 1183	g/sm ³	1,05±0,01
Erish oqimi tezligi (220°C, 10kg)	ISO 1133	g/10daq	≥21
Kirishish (qoliplashdan 48 soat keyin)	ISO 294	%	0,4 dan 0,7 gacha
Mexanik xususiyatlar			
Cho'zilishdagi oquvchilik kuchlanishi	ISO 527	MPa	≥45
Egilish moduli	ISO 178	MPa	≥2200
Kertikli Charpi zarbasi (23°C)	ISO 179-1	kJ/m ²	≥20
Kertikli Charpi zarbasi (-30°C)	ISO 179-1	kJ/m ²	≥10
Rokvell qattiqligi	ISO 2039	R-shkala	110
Issiqlik xususiyatlari			
Vikat yumshatish harorati	ISO 306	°C	≥90
HDT (1,8 MPa)	ISO 75	°C	≥78

Ishlov berish yo'riqnomasi (injeksiya qoliplash)

Ishlov berish parametrlari		O'lchov birligi	Qiymatlar
Quritish harorati		°C	80
Quritish vaqti		soat	3-4
Minimal namlik darajasi		%	0,3
Erish harorati		°C	220 ~ 250
Silindr harorati	Orqa qism	°C	200 ~ 210
	O'rta qism	°C	210 ~ 230
	Old qism	°C	225 ~ 250
Sople harorati		°C	225 ~ 250
Qolip harorati		°C	50 ~ 95
Qayta bosim		Bar	3,0 ~ 15

"UzAuto CEPLA" MCHJ XK laboratoriyasi